

Certificate of Testing




# CAPITAL RUBBER CORP

Order No.:  
Serial No.:  
Size:  
Length:

Test Number: 1201  
Test Date: 10/01/19  
Description: Lot # 147 3/32" CA  
Test Method: BREAK

Peak Load: 830 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

Certificate of Testing




# CAPITAL RUBBER CORP

Test Number: 1329  
Test Date: 05/28/21  
Description: Lot 212 1/8" Galvanized  
Test Method: BREAK

Order No.:  
Serial No.:  
Size:  
Length:

Peak Load: 1,716 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

A handwritten signature in black ink, appearing to be 'Steve G.', followed by a horizontal line.

Certificate of Testing




# CAPITAL RUBBER CORP

Order No.: CC19  
Serial No.:  
Size: 0.1875 inches  
Length: 24 inches

Test Number: 1104  
Test Date: 02/13/19  
Description: LOT # 133  
Test Method: BREAK

Peak Load: 3,384 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:  
  
Steve Beeson

Certificate of Testing




# CAPITAL RUBBER CORP

Order No.: CC25  
Serial No.:  
Size:  
Length:

Test Number: 1273  
Test Date: 06/16/20  
Description: Lot # 186 CC1/4"  
Test Method: BREAK

Peak Load: 6,404 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

Steve Beeson

Certificate of Testing




# CAPITAL RUBBER CORP

Test Number: 1121  
Test Date: 04/22/19  
Description: Lot # 122 ( 5/16" Cable)  
Test Method: BREAK

Order No.:  
Serial No.:  
Size:  
Length:

Peak Load: 10,398 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

A handwritten signature in black ink, appearing to be 'Steve G.', is written over a horizontal line.

Certificate of Testing




# CAPITAL RUBBER CORP

Test Number: 1356  
Test Date: 08/27/21  
Description: Lot# 220 CC 3/8" Galvanized  
Test Method: BREAK

Order No.:  
Serial No.:  
Size:  
Length:

Peak Load: 13,212 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

Certificate of Testing




# CAPITAL RUBBER CORP

Order No.:  
Serial No.:  
Size:  
Length:

Test Number: 1332  
Test Date: 05/28/21  
Description: Lot 213 7/16" Galvanized  
Test Method: BREAK

Peak Load: 18,166 lbs.




Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

A handwritten signature in black ink, appearing to be 'Steve G.', written over a horizontal line.

Certificate of Testing




# CAPITAL RUBBER CORP

Test Number: 1357  
Test Date: 09/07/21  
Description: Lot 221 1/2" Galvanized  
Test Method: BREAK

Order No.:  
Serial No.:  
Size:  
Length:

Peak Load: 24,246 lbs.



Test Results  
 Acceptable  
 Not Acceptable

Conducted by:

A handwritten signature in black ink, appearing to be 'Steve G.', written over a horizontal line.